



Titacon GF915

RESIN : POLYACETAL RESIN

PRODUCT DESCRIPTION : 15%GLASS FIBER FILLED, HIGH STRENGTH/STIFFNESS.

Properties	Unit	method	Value
Color	-	-	Natural
specific gravity	g/cm ³	ISO 1183	1.51
Tensile strength	MPa	ISO	100
Tensile Elongation		527-1,2	>3
Flexural strength	MPa	ISO 178	150
Flexural modulus			6200
Charpy impact strength(notched)	kJ/m ²	ISO	7
		179/1eA	
Heat Deflection Temperature(1.8MPa)	°C	ISO	145
		75-1,2	
Volume resistivity	Ω•cm	IEC 60093	1×10 ¹⁵
Surface resistivity	Ω		1×10 ¹⁴
Flammability		UL 94	HB
Mold shrinkage	%	50x70x3	0.8~1.3
		mmt	
MOLDING CONDITION			
	°C	Drying	100x 3Hrs
		Melt Temp.	170~200
Mold Temp.		60~100	
	%	Inject. Press.	30~70
		Inject. Velocity	20~50

*All property values shown in this data sheet are the representative values and not minimum value of this material.