



Titacon GB925

RESIN : POLYACETAL RESIN

PRODUCT DESCRIPTION : 25%GLASS BEADS FILLED, DIMENSIONAL ACCURACY, LOWER WARPAGE.

Properties	Unit	method	Value
Color	-	-	Nature
specific gravity	g/cm ³	ISO 1183	1.59
Tensile strength	MPa	ISO	60
Tensile Elongation		527-1,2	>10
Flexural strength	MPa	ISO 178	104
Flexural modulus			3800
Charpy impact strength(notched)	kJ/m ²	ISO	3.50
		179/1eA	
Heat Deflection Temperature(1.8MPa)	°C	ISO	125
		75-1,2	
Volume resistivity	Ω•cm	IEC 60093	5×10 ¹⁴
Surface resistivity	Ω		5×10 ¹⁵
Flammability		UL 94	HB
Mold shrinkage	%	50x70x3	1.2~1.4
		mmt	
MOLDING CONDITION	°C	Drying	100x 3Hrs
		Melt Temp.	170~200
		Mold Temp.	60~100
	%	Inject. Press.	30~70
Inject. Velocity		20~50	

*All property values shown in this data sheet are the representative values and not minimum value of this material.