



## Titalon 2320

RESIN : POLYAMIDE66 RESIN

PRODUCT DESCRIPTION : 30%GLASS BEAD FILLED, 20%PTFE FILLED,  
SLIDING, WEAR RESISTANCE

Properties	Unit	method	Value
Color	-	-	Natural
specific gravity	g/cm <sup>3</sup>	ISO 1183	1.48
Tensile strength	MPa	ISO	55
Tensile Elongation		527-1,2	>2
Flexural strength	MPa	ISO 178	96
Flexural modulus			2900
Charpy impact strength(notched)	kJ/m <sup>2</sup>	ISO 179/1eA	2.50
Heat Deflection Temperature (1.8MPa)	°C	ISO 75-1,2	180
Volume resistivity	Ω•cm	IEC 60093	1×10 <sup>14</sup>
Surface resistivity	Ω		1×10 <sup>14</sup>
Flammability		UL 94	HB
Mold shrinkage	%	50x70x3 mmt	1.4~1.8
MOLDING CONDITION			
MOLDING CONDITION	°C	Drying	80~100x 4Hrs
		Melt Temperature	260~290
		Mold Temperature	60~100
	%	Inject. Pressure	30~70
		Inject. Velocity	30~60

\*All property values shown in this data sheet are the representative values and not minimum value of this material.